



Matthews Paint Product Reference Guide: Conventional Gloss

Conventional Gloss Intermix Colors 90° Gloss + / -5°

SOA202SP White	SOA911SP Violet	SOA912SP Maroon	SOA913SP Magenta	SOA914SP Dark Red	SOA915SP Red Oxide	SOA917SP Yellow Oxide	SOA920SP Blue
SOA921SP Green	SOA923SP Black	SOA925SP New Blue	SOA929SP Carbon Black	SOA930SP Light Red	SOA940SP Red Yellow	SOA942SP Green Yellow	SOA947SP Scarlet Red

Because of variations in monitors and printers, the colors shown above may vary from the actual toner colors.

Catalyst Options:

- **43270SP** for spray application
- **43999SP** for spray applications requiring a slower dry time
- **43621SP** for brush or roll applications (Metallic paints are not recommended for brush or roll applications.)

Reducer Options

- **6379SP** = Fast for cool weather applications not lower than 60-75°
- **45280SP** = Warm temp reducer for applications in temps between 70-80°
- **45290SP** = Hot weather applications with temps between 75-85°
- **6396SP** = Extreme Hot weather applications 85° and above
- **45251SP** = Retarder reducer must be used with 6396SP, to use this product; mix the 6396SP with the 45251SP 1:1, from that mixture; mix your paint, catalyst, 6396SP/45251SP combo as such, 3 parts paint, 1 part catalyst, 1 part 6396SP/45251SP reducer combo

*Add in Sequential order based on percentages used in formulas.

Mix ratio = 3:1:1 (3=paint, 1=catalyst, 1= reducer)



Matthews Paint Product Reference Guide: Conventional Gloss

Conventional Gloss Intermix Colors 90° Gloss + / -5° with Metallic Colors

SOA202SP White	SOA911SP Violet	SOA912SP Maroon	SOA913SP Magenta	SOA914SP Dark Red	SOA915SP Red Oxide	SOA917SP Yellow Oxide	SOA920SP Blue
SOA921SP Green	SOA923SP Black	SOA925SP New Blue	SOA929SP Carbon Black	SOA930SP Light Red	SOA931SP Trans Red Oxide	SOA932SP Trans Yellow Oxide	SOA940SP Red Yellow
SOA942SP Green Yellow	SOA947SP Scarlet Red	SOA951SP Medium Silver	SOA952SP Sparkle Silver	SOA953SP Super Sparkle Silver	SOA954SP Fine Silver		

Because of variations in monitors and printers, the colors shown above may vary from the actual toner colors.

Catalyst Options:

- **43270SP** for spray application
- **43999SP** for spray applications requiring a slower dry time
- **43621SP** for brush or roll applications (Metallic paints are not recommended for brush or roll applications.)

Reducer Options

- **6379SP** = Fast for cool weather applications not lower than 60-75°
- **45280SP** = Warm temp reducer for applications in temps between 70-80°
- **45290SP** = Hot weather applications with temps between 75-85°
- **6396SP** = Extreme Hot weather applications 85° and above
- **45251SP** = Retarder reducer must be used with 6396SP, to use this product; mix the 6396SP with the 45251SP 1:1, from that mixture; mix your paint, catalyst, 6396SP/45251SP combo as such, 3 parts paint, 1 part catalyst, 1 part 6396SP/45251SP reducer.

*Add in Sequential order based on percentages used in formulas.

Mix ratio = 3:1:1 (3=paint, 1=catalyst, 1= reducer)